



## Pressed Eye Shadow "Metallic Anthracite" with AGENAFLO OS 9051

"Formulated and developed by ECKART GmbH"

Ingredients	INCI-Name	%w/w	Supplier
-------------	-----------	------	----------

### Phase A

Talc Powder	Talc	29,00	www.vwr.com
<b>AGENAFLO OS 9051</b>	<b>Aluminum Starch Octenylsuccinate</b>	<b>8,00</b>	<b>www.agrana.com</b>
Kaolin	Kaolin	10,00	www.sigmaaldrich.com
Synafil S 1050	Synthetic Fluorophopite	10,00	www.eckart.net
Visionaire Bright Splendid Champagne	Aluminum Powder (and) Aluminum Hydroxide (and) Silica	15,00	www.eckart.net
Syncrystal Soft Black	Synthetic Fluorophlogopite (and) Iron Oxides	15,00	www.eckart.net

### Phase B

Xiameter PMX- 0345 Cyclosiloxane	Cyclomethicone	4,00	www.dowcorning.com
Ewalan IP	Isopropyl Lanolate	5,00	www.wagnerlanolin.de
MOD	Octyldodecyl Myristate	4,00	www.gattefosse.com

### PROCEDURE

1. Weigh in phase A.
2. Add phase B and stir until homogenous.
3. Press eye shadow at 100 bar for 30 s.

This formulation is indicative only and no responsibility whatsoever will be assumed. This formulation is offered solely for your consideration, investigation and verification. It is your responsibility to thoroughly test any formulations before use. All those who use our formulations as well as those who process AGRANA Starches are themselves entirely responsible for the adherence to prevailing statutory regulations and the observance of patent rights as well as other protective rights for other companies. AGRANA does not assure any liability with respect to the composition of the formulation or the use in products.