



Compact Bronzing Powder - "Summery Look" with AGENAFLO OS 9051

"Formulated and developed by ECKART GmbH"

Ingredients	INCI-Name	%w/w	Supplier
-------------	-----------	------	----------

Phase A

Talc Powder	Talc	34,00	www.vwr.com
AGENAFLO OS 9051	Aluminum Starch Octenylsuccinate	10,00	www.agrana.com
Phycorail	Corallina Officinalis Extract	1,00	www.seppic.com
Synafil S 1050	Synthetic Fluorophopite	15,00	www.eckart.net
Tixogel- VP V XR	Quaternium- 90 Bentonite	3,00	www.byk.com
Syncrystal Soft Copper	Synthetic Fluorophlogopite (and) Iron Oxides	8,00	www.eckart.net
Syncrystal Soft Black	Synthetic Fluorophlogopite (and) Iron Oxides	2,00	www.eckart.net
Mirage Champagne	Calcium Sodium Borosilicate (and) Iron Oxides	15,00	www.eckart.net

Phase B

Ceraphyl 847	Octyldodecyl Stearoyl Stearate	3,00	www.ashland.com
Xiameter PMX-200 Silicone Fluid 10 cs	Dimethicone	4,00	www.dowcorning.com
Xiameter PMX- 0345 Cyclosiloxane	Cyclomethicone	3,00	www.dowcoming.com
Softisan 649	Bis- Diglyceryl Polyacyladipate-2	2,00	www.sasolwax.com

PROCEDURE

1. Weigh in phase A with speedmixer (30s/2000 rpm).
2. Add the ingredients of phase B to phase A.
3. Mix again with speedmixer (30s/ 2200 rpm).
4. Press the powder at 100 bar for 30 s.

This formulation is indicative only and no responsibility whatsoever will be assumed. This formulation is offered solely for your consideration, investigation and verification. It is your responsibility to thoroughly test any formulations before use. All those who use our formulations as well as those who process AGRANA Starches are themselves entirely responsible for the adherence to prevailing statutory regulations and the observance of patent rights as well as other protective rights for other companies. AGRANA does not assure any liability with respect to the composition of the formulation or the use in products.