

DRAPING – “Pressed Blush” 10

“Formulated and developed by ECKART GmbH”
Ref. CC/2483/EU

Ingredients	INCI-Name	%w/w	Supplier
Phase A			
Talc Powder	Talc	30,30	www.vwr.com
AGENAFLO OS 9051	Aluminum Starch Octenylsuccinate	10,00	www.agrana.com
Synafil S1050	Synthetic Fluorphlogopite	25,70	www.eckart.net
Syncrystal Soft Copper	Synthetic Fluorphlogopite (and) Iron Oxides	10,00	www.eckart.net
Syncrystal Fire-Red	Synthetic Fluorphlogopite (and) Iron Oxides	10,00	www.eckart.net
Phase B			
Xiameter PMX- 0345 Cyclosiloxane	Cyclomethicone	4,00	www.dowcoming.com
Ewalan IP	Isopropyl Lanolate	6,00	www.wagnerlanolin.de
Ceraphyl 847	Octyldodecyl Stearoyl Stearate	4,00	www.ashland.com

PROCEDURE

1. Weigh in phase A
2. Add phase B and stir until homogeneous
3. Press the powder at 100 bar for 30 s.



This formulation is indicative only and no responsibility whatsoever will be assumed. This formulation is offered solely for your consideration, investigation and verification. It is your responsibility to thoroughly test any formulations before use. All those who use our formulations as well as those who process AGRANA Starches are themselves entirely responsible for the adherence to prevailing statutory regulations and the observance of patent rights as well as other protective rights for other companies. AGRANA does not assure any liability with respect to the composition of the formulation or the use in products.