

AGRANA STARCH

AGRANA - Draping Powder with AGENAFLO OS 9051.doc release 01, 15.02.2018 Page 1 of 1

DRAPING – "Draping Powder"

"Formulated and developed by ECKART GmbH" Ref. CC/2484/EU

Ingredients INCI-Name %w/w Supplier

Phase A

i iluse A			
Talc Powder	Talc	30,30	www.vwr.com
AGENAFLO OS 9051	Aluminum Starch Octenylsuccinate	10,00	www.agrana.com
Synafil S1050	Synthetic Fluorphlogopite	20,00	www.eckart.net
Synafil W1234	Polypropylene	5,00	www.eckart.net
Syncrystal Red	Synthetic Fluorphlogopite (and) Titanium	10,00	www.eckart.net
	Dioxide (and) Tin Oxide		
Syncrystal Ivory	Synthetic Fluorphlogopite (and) Titanium	5,00	www.eckart.net
	Dioxide (and) Iron Oxides (and) Tin Oxide		
Syncrystal Soft Peach	Synthetic Fluorphlogopite (and) Titanium	5,00	www.eckart.net
	Dioxide (and) Iron Oxides (and) Tin Oxide		
Red 6 Lake (CI 15850)	Red 6 Lake	0,70	

Phase B

Xiameter PMX-0345 Cyclosiloxane	Cyclomethicone	4,00	www.dowcoming.com
Ewalan IP	Isopropyl Lanolate	6,00	www.wagnerlanolin.de
Ceraphyl 847	Octyldodecyl Stearoyl Stearate	4,00	www.ashland.com

PROCEDURE

- 1. Weigh in phase A
- 2. Add phase B and stir until homogeneous
- 3. Press the powder at 100 bar for 30 s.



This formulation is indicative only and no responsibility whatsoever will be assumed. This formulation is offered solely for your consideration, investigation and verification. It is your responsibility to thoroughly test any formulations before use. All those who use our formulations as well as those who process AGRANA Starches are themselves entirely responsible for the adherence to prevailing statutory regulations and the observance of patent rights as well as other protective rights for other companies. AGRANA does not assure any liability with respect to the composition of the formulation or the use in products.