

Loose Finishing Powder – “Silk” with AGENAFLO OS 9051

“Formulated and developed by ECKART GmbH”

Ingredients	INCI-Name	%w/w	Supplier
Phase A			
SYNAFIL S115	Synthetic Fluorophopite	20.00	www.eckart.net
SYNAFIL S1050	Synthetic Fluorophopite	35.00	www.eckart.net
SYNAFIL W1234	Polypropylene	6.00	www.eckart.net
SYNCRYSTAL Silk Silver	Synthetic Fluorophlogopite (and) Titanium Dioxide (and) Tin Oxide	5.00	www.eckart.net
AGENAFLO OS 9051	Aluminium Starch Octenylsuccinate	15.00	www.agrana.com
Talc Powder	Talc	19.00	www.vwr.com

PROCEDURE

1. Mix phase A with speedmixer (30s/ 2000 rpm)
2. Fill into an appropriate container



This formulation is indicative only and no responsibility whatsoever will be assumed. This formulation is offered solely for your consideration, investigation and verification. It is your responsibility to thoroughly test any formulations before use. All those who use our formulations as well as those who process AGRANA Starches are themselves entirely responsible for the adherence to prevailing statutory regulations and the observance of patent rights as well as other protective rights for other companies. AGRANA does not assure any liability with respect to the composition of the formulation or the use in products.