

Everlasting Regenerist Foundation with AGENAFLO OS 9051

"Formulated and developed by Owen Trading"

Ingredients	INCI-Name	%w/w	Supplier
Phase A			
Silube J208-812 CG	Lauryl PEG-8 dimethicone	3,00	Siltech
Silube T308-16-TT	Cetyl PEG/PPG-10/1 dimethicone	1,50	Siltech
Isododecane	Isododecane	12,00	
Silmer Q20	Trimethylsiloxysilicate	2,00	Siltech
Parsol MCX	Ethylhexyl Methoxycinnamate	4,00	
Rofetan PGCC	Propylene Glycol Dicaprylate/ Dicaprate	3,00	Ecogreen
Sitech CE-2000	Trioctyldodecyl Citrate	3,00	Siltech
Silmer G-162-F5	Dimethicone (and) Dimethicone / Vinyl Dimethicone Crosspolymer	5,00	Siltech
Silwax D-02	Ethyl Methicone	2,00	Siltech
Sipernat 11PC	Hydrated Silica	2,00	Evonik
Clytone HY	Quaternium-18 Bentonite	0,50	BYK
TiO2 CR-50 (AS)	Titanium Dioxide	7,00	
Iron oxide yellow (AS)	Iron oxide yellow	0,56	
Iron oxide red (AS)	Iron oxide red	0,43	
Iron oxide black (AS)	Iron oxide black	0,25	
Performix CC	Lecithin, Caprylic/Capric Glycerides Polyglycerin-10 Esters	0,50	ADM
Silwax CR-5016	Cetyl dimethicone/bis vinyl dimethicone crosspolymer	1,00	Siltech
Ryoto Sugar Ester O0170	Sucrose Polyoleate (and) Tocopherol	0,20	Mitsubishi
Permalene M 70 wax	Synthetic Wax	1,00	New Phase
Phase B			
Water	Water	To 100,00	
NaCl	Sodium Chloride	1,00	
Glycerin	Glycerin	20,00	
Laponite XLS	Lithium magnesium sodium silicate (and) tetrasodium pyrophosphate	5,00	
Propylene Glycol	Propylene Glycol		ADM



Phase C

Preservatives	Preservatives	0,50	
AGENAFLO OS 9051	Aluminum Starch Octenylsuccinate	5,00	AGRANA

PROCEDURE

1. Wet the Pigment with the liquid oil of phase A.
2. Add the remaining ingredients of Phase A and mix well. Then heat to completely melt and keep temperature at 80°C.
3. Phase B: Disperse Laponite XLS in water at high speed stirring for 10-15 min to form a uniform liquid. Then add the other ingredient of phase B, mix well and heat to 80°C.
4. Slowly add the phase B to phase A, with the high speed 1300 rpm stirring for 5 min.
5. Cool down to 45°C, add Phase C and mix well.

This formulation is indicative only and no responsibility whatsoever will be assumed. This formulation is offered solely for your consideration, investigation and verification. It is your responsibility to thoroughly test any formulations before use. All those who use our formulations as well as those who process AGRANA Starches are themselves entirely responsible for the adherence to prevailing statutory regulations and the observance of patent rights as well as other protective rights for other companies. AGRANA does not assure any liability with respect to the composition of the formulation or the use in products.