

Pressed Eyeshadow "Hippi Brown" with AGENAFLO OS 9051

"Formulated and developed by Eckart GmbH"

Ingredients	INCI-Name	%w/w	Supplier
Phase A			
Talc Powder	Talc	32,00	www.vwr.com
AGENAFLO OS 9051	Aluminum Starch Octenylsuccinate	8,00	www.agrana.com
Softouch CC6004	Boron Nitride	6,00	www.momentive.com
SYNAFIL S 1050	Synthetic Fluorophlopite	12,00	www.eckart.net
SYNCRYSTAL Soft Bronze	Synthetic Fluorophlogopite (and) Iron Oxides	20,00	www.eckart.net
VISIONAIRE Sunflower Gold	Bronze Powder (and) Silica	10,00	www.eckart.net
Phase B			
Xiameter PMX-0345 Cyclosiloxane	Cyclomethicone	4,00	www.dowcorning.com
Ewalan IP	Isoprpyl Lanolate	4,00	www.wagnerlanolin.de
MOD	Octyldodecyl Myristate	4,00	www.gattefosse.com

PROCEDURE

1. Weigh in phase A
2. Add phase B and stir until homogeneous
3. Press eye shadow at 100 bar for 30 s



This formulation is indicative only and no responsibility whatsoever will be assumed. This formulation is offered solely for your consideration, investigation and verification. It is your responsibility to thoroughly test any formulations before use. All those who use our formulations as well as those who process AGRANA Starches are themselves entirely responsible for the adherence to prevailing statutory regulations and the observance of patent rights as well as other protective rights for other companies. AGRANA does not assure any liability with respect to the composition of the formulation or the use in products.