

## Metallic Pressed Eye Shadow – “Reflective Silver” with AGENAFLO OS 9051

“Formulated and developed exclusively by Eckart GmbH”

**Ingredients**                      **INCI-Name**                      **%w/w**    **Supplier**

### Phase A

Talc Powder	Talc	28,00	<a href="http://www.vwr.com">www.vwr.com</a>
<b>AGENAFLO OS 9051</b>	<b>Aluminium Starch Octenylsuccinate</b>	<b>8,00</b>	<a href="http://www.agrana.com">www.agrana.com</a>
Lyponyl 20-LL	Nylon 12 (and) Lauroyl Lysine	10,00	<a href="http://www.lipochemicals.com">www.lipochemicals.com</a>
SYNAFIL S 1050	Synthetic Fluorophlopite	7,00	<a href="http://www.eckart.net">www.eckart.net</a>
VISIONAIRE Bright Silver Sea	Aluminum Powder (and) Silica	30,00	<a href="http://www.eckart.net">www.eckart.net</a>

### Phase B

Xiameter PMX-0345 Cyclosiloxane	Cyclomethicone	4,00	<a href="http://www.dowcorning.com">www.dowcorning.com</a>
Ewalan IP	Isopropyl Lanolate	9,00	<a href="http://www.wagnerlanolin.de">www.wagnerlanolin.de</a>
MOD	Octyldodecyl Myristate	4,00	<a href="http://www.gattefosse.com">www.gattefosse.com</a>



### PROCEDURE

1. Weigh in phase A.
2. Add phase B and stir until homogeneous.
3. Press eye shadow at 100bar for 30s.

### Stability:

Drop test passed.

This formulation is indicative only and no responsibility whatsoever will be assumed. This formulation is offered solely for your consideration, investigation and verification. It is your responsibility to thoroughly test any formulations before use. All those who use our formulations as well as those who process AGRANA Starches are themselves entirely responsible for the adherence to prevailing statutory regulations and the observance of patent rights as well as other protective rights for other companies. AGRANA does not assure any liability with respect to the composition of the formulation or the use in products.